

1. Device Name	NEO HEAT 350																																									
2. Description	Neoprene, Grip Pattern, Heat Resistant, Cut Resistant, Seamless Kevlar® Lining, Excellent protection from cuts and abrasions, Excellent Dexterity, High Resistance to Acids, 33cm Length, 2.1mm Thickness																																									
3. Product Codes & Sizes	<table border="1"> <thead> <tr> <th>Product Code</th> <th>Size</th> <th>Single Barcode</th> <th>Shipper Barcode</th> </tr> </thead> <tbody> <tr> <td>41285</td> <td>10</td> <td>9311059412852</td> <td>29311059412856</td> </tr> </tbody> </table>			Product Code	Size	Single Barcode	Shipper Barcode	41285	10	9311059412852	29311059412856																															
Product Code	Size	Single Barcode	Shipper Barcode																																							
41285	10	9311059412852	29311059412856																																							
4. Recommended Applications	<table border="0"> <tr> <td> <ul style="list-style-type: none"> • Casting • Moulding • Ceramic Industry • Cement Industry • Kitchens • Bakeries </td> <td> <ul style="list-style-type: none"> • Car Industry • Mechanic Workshop • Galvanising Industry • Construction • Manufacturing • Beverage Industry </td> <td> <ul style="list-style-type: none"> • Chemical Processing • Food Processing • Food Manufacturing • Industrial • Maintenance </td> </tr> </table>			<ul style="list-style-type: none"> • Casting • Moulding • Ceramic Industry • Cement Industry • Kitchens • Bakeries 	<ul style="list-style-type: none"> • Car Industry • Mechanic Workshop • Galvanising Industry • Construction • Manufacturing • Beverage Industry 	<ul style="list-style-type: none"> • Chemical Processing • Food Processing • Food Manufacturing • Industrial • Maintenance 																																				
<ul style="list-style-type: none"> • Casting • Moulding • Ceramic Industry • Cement Industry • Kitchens • Bakeries 	<ul style="list-style-type: none"> • Car Industry • Mechanic Workshop • Galvanising Industry • Construction • Manufacturing • Beverage Industry 	<ul style="list-style-type: none"> • Chemical Processing • Food Processing • Food Manufacturing • Industrial • Maintenance 																																								
5. Materials	Neoprene, Kevlar® Seamless Liner, Does not contain DOP/DEHP phthalates																																									
6. Standards & Approvals	<div style="display: flex; align-items: center;"> <div style="margin-right: 10px;"> </div> <div style="margin-right: 10px;"> </div> <div style="margin-right: 10px;"> </div> <div style="margin-right: 10px;"> </div> </div> <p>Neo Heat 350 are tested to and complies with;</p> <ul style="list-style-type: none"> • <i>Conforms to European Council Directive 89/686/EEC relating to (Complex Design) Personal Protective Equipment after assessment against standards</i> <ul style="list-style-type: none"> - EN374:2003 - EN388:2003 - EN407:2004 																																									
7. Dimensions	<table border="1"> <thead> <tr> <th>SIZE</th> <th>LENGTH (+/-10mm)</th> <th>THICKNESS SINGLE WALL (+/-0.1mm)</th> <th>CIRCUMFRENCE PALM (+/-5mm)</th> </tr> </thead> <tbody> <tr> <td>10</td> <td>330mm</td> <td>1.9mm</td> <td>268mm</td> </tr> </tbody> </table>			SIZE	LENGTH (+/-10mm)	THICKNESS SINGLE WALL (+/-0.1mm)	CIRCUMFRENCE PALM (+/-5mm)	10	330mm	1.9mm	268mm																															
SIZE	LENGTH (+/-10mm)	THICKNESS SINGLE WALL (+/-0.1mm)	CIRCUMFRENCE PALM (+/-5mm)																																							
10	330mm	1.9mm	268mm																																							
8. Colour	Black with Yellow Kevlar® Lining																																									
9. Performance Requirements	<table border="1"> <thead> <tr> <th>CHARACTERISTICS</th> <th>LEVEL ACHIEVED</th> <th>REFERENCE STANDARD</th> </tr> </thead> <tbody> <tr> <td>Abrasion Resistance</td> <td>3</td> <td>EN388:2003 clause 6.1</td> </tr> <tr> <td>Blade Cut Resistance</td> <td>5</td> <td>EN388:2003 clause 6.2</td> </tr> <tr> <td>Tear Resistance</td> <td>4</td> <td>EN388:2003 clause 6.3</td> </tr> <tr> <td>Puncture Resistance</td> <td>3</td> <td>EN388:2003 clause 6.4</td> </tr> <tr> <td>Air Leak Test</td> <td>PASS</td> <td>EN374 Micro O Risks</td> </tr> <tr> <td>Water Leak Test</td> <td>PASS</td> <td>EN374 Micro O Risks</td> </tr> <tr> <td>n-Heptane, 40%</td> <td>3</td> <td>EN374 Chemical Risks</td> </tr> <tr> <td>Sodium Hydroxide 40%</td> <td>6</td> <td>EN374 Chemical Risks</td> </tr> <tr> <td>Sulphuric Acid 96%</td> <td>6</td> <td>EN374 Chemical Risks</td> </tr> <tr> <td>Acetic acid, glacial</td> <td>6</td> <td>EN374 Chemical Risks</td> </tr> <tr> <td>Methanol</td> <td>6</td> <td>EN374 Chemical Risks</td> </tr> <tr> <td>Burning Behaviour</td> <td>4</td> <td>EN407 Thermal Risks</td> </tr> </tbody> </table>			CHARACTERISTICS	LEVEL ACHIEVED	REFERENCE STANDARD	Abrasion Resistance	3	EN388:2003 clause 6.1	Blade Cut Resistance	5	EN388:2003 clause 6.2	Tear Resistance	4	EN388:2003 clause 6.3	Puncture Resistance	3	EN388:2003 clause 6.4	Air Leak Test	PASS	EN374 Micro O Risks	Water Leak Test	PASS	EN374 Micro O Risks	n-Heptane, 40%	3	EN374 Chemical Risks	Sodium Hydroxide 40%	6	EN374 Chemical Risks	Sulphuric Acid 96%	6	EN374 Chemical Risks	Acetic acid, glacial	6	EN374 Chemical Risks	Methanol	6	EN374 Chemical Risks	Burning Behaviour	4	EN407 Thermal Risks
CHARACTERISTICS	LEVEL ACHIEVED	REFERENCE STANDARD																																								
Abrasion Resistance	3	EN388:2003 clause 6.1																																								
Blade Cut Resistance	5	EN388:2003 clause 6.2																																								
Tear Resistance	4	EN388:2003 clause 6.3																																								
Puncture Resistance	3	EN388:2003 clause 6.4																																								
Air Leak Test	PASS	EN374 Micro O Risks																																								
Water Leak Test	PASS	EN374 Micro O Risks																																								
n-Heptane, 40%	3	EN374 Chemical Risks																																								
Sodium Hydroxide 40%	6	EN374 Chemical Risks																																								
Sulphuric Acid 96%	6	EN374 Chemical Risks																																								
Acetic acid, glacial	6	EN374 Chemical Risks																																								
Methanol	6	EN374 Chemical Risks																																								
Burning Behaviour	4	EN407 Thermal Risks																																								



CHARACTERISTICS	LEVEL ACHIEVED	REFERENCE STANDARD
Contact Heat	3	EN407 Thermal Risks
Convective Heat	3	EN407 Thermal Risks
Radiant Heat	2	EN407 Thermal Risks
Small Splashes of Molten Metal	4	EN407 Thermal Risks
Large Quantities of Molten Metal	X	EN407 Thermal Risks

10. Quality Control Inspection Procedures

a) For the inspection of visual defects, random samples are drawn from the lot at the stage of packing. Sample is visually inspected for major and minor defects and status of test is determined based on the acceptance criteria.
 b) One glove is measured from each lot for dimensions and compared with specifications. If any dimension is found to be nonconforming, a random sample is drawn from the lot as per sampling plan. Status of the test is determined based on the acceptance criteria.
 c) For the inspection of packaging defects, random samples are drawn from the lot at the stage of packing. Sample is visually inspected for a major and minor defect and status is determined based on the acceptance criteria.
 d) If all above tests are PASS, the status of the lot is considered as "PASS". Otherwise the status of the lot is considered "HOLD".
 e) HOLD lots are re-inspected and a subsequent QC check is performed on such lots. Status of such lots is determined based on the same method described above.
 f) PASS lots are transferred to Finished Goods Store ready for shipment.

11. Packaging

1pair will be packed into a clear polybag with label. 24 pairs per export quality shipper carton (outer).

12. Shipper Carton Specifications

SIZE	LENGTH (mm)	WIDTH (mm)	HEIGHT (mm)	GROSS WEIGHT (kg)
10	270	160	200	7.7

13. Storage Conditions

The gloves will maintain their properties when stored in dry conditions out of direct sunlight at between 10 to 30°c

14. Shelf Life

The gloves shall retain the above physical properties for a period of 3 years from the date of manufacture when stored in compliance with the above storage conditions before deterioration occurs.

Product Code **41285** Size **10**

NEO HEAT 350

Neoprene coated glove, ideal for hot liquids
 Level 3 Resistance to Contact Heat
 Level 5 Cut Resistant Protection

FEATURES

- Liquid proof neoprene layer (reusable)
- Grip pattern on glove to ensure secure grip in both wet and dry conditions
- Level 3 resistance to contact heat
- Level 5 cut resistance protection
- Seamless Kevlar® lining provides excellent protection from cuts and abrasion hazards
- Glove will resist burning from inadvertent small splashes of molten metals
- High resistance to acids
- Excellent dexterity
- 330mm long and 2.1mm thick

APPLICATIONS

- Casting / Moulding
- Ceramic / Cement industries
- Industrial / Domestic kitchens
- Bakeries
- Power and energy

Made in Sri Lanka for
 RCR International Pty Ltd
 ABN 21 089 270 360
 www.rcr.com.au

9 311059 412852